


# TECHNICAL CHARACTERISTICS

## wineo 800 wineo

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

	wineo 800 wood	wineo 800 wood XL	wineo 800 stone XL	wineo 800 tile L / XL / XXL	wineo 800 craft
<b>Format</b>	1200 x 180 mm	1505 x 235 mm	914.4 x 457.2 mm	457.2 x 457.2 mm 914.4 x 457.2 mm 914.4 x 914.4 mm	457.2 x 457.2 mm 914.4 x 101.6 mm
<b>Product thickness</b>	2.5 mm	2.5 mm	2.5 mm	2.5 mm	2.5 mm
<b>Planks, tiles / m<sup>2</sup> per box</b>	16 / 3.46 m <sup>2</sup>	12 / 4.24 m <sup>2</sup>	10 / 4.18 m <sup>2</sup>	16 / 3.34 m <sup>2</sup> 10 / 4.18 m <sup>2</sup> 6 / 5.02 m <sup>2</sup>	16 / 3.34 m <sup>2</sup> 20 / 1.86 m <sup>2</sup>
<b>Boxes / m<sup>2</sup> per pallet</b>	75 / 259.20 m <sup>2</sup>	60 / 254.40 m <sup>2</sup>	40 / 167.20 m <sup>2</sup>	52 / 173.68 m <sup>2</sup> 40 / 167.20 m <sup>2</sup> 37 / 185.74 m <sup>2</sup>	52 / 173.68 m <sup>2</sup> 135 / 251.10 m <sup>2</sup>
<b>Guarantee</b>	25 years – Guarantee for private use according to Windmüller warranty conditions – www.wineo.de				



Classification		Product composition
<b>Utilization class 23</b> EN ISO 10874	Heavy-duty use in the domestic area	1 <b>Surface sealing</b>
<b>Utilization class 33</b> EN ISO 10874	Heavy-duty use in the commercial sector	2 <b>Surface texture</b> Various embossings
<b>Utilization class 42</b> EN ISO 10874	Normal use in the light industrial sector	3 <b>Wear layer</b> Thickness 0.55 mm
Wear layer binder content EN ISO 10582	Type I	4 <b>Decor</b> Decor film
<b>R10</b> Anti slip category DIN 51130	R 10	5 <b>Base layer</b>
<b>Staining and chemical resistance</b> EN ISO 26987	Good resistance according to the concentration and residence time	6 <b>Backing</b>
<b>Light fastness</b> EN ISO 105-B02	Light fastness (method 2) ≥ 6	<b>DESIGN FLOORING to glue</b>
<b>Residual indentation</b> EN ISO 24343-1	≤ 0.1 mm without insulation mat ~ 0.17 mm with insulation mat silentPREMIUM	wood – bevelled edge tile – bevelled edge
<b>Castor chair test</b> ISO 4918	25000 revolutions no damage with rolls type W	 <b>70 710 4061-3</b> <a href="http://www.proficert.com">www.proficert.com</a>  <b>tested for emissions, harmful substances</b> <b>PREMIUM</b>
<b>Thermal resistance</b> EN 12667	≤ 0.015 (m <sup>2</sup> K)/W without insulation mat ≤ 0.025 (m <sup>2</sup> K)/W with insulation mat silentPREMIUM	
<b>Impact sound reduction</b> EN ISO 16251-1	~ 4 dB	
<b>Dimension stability</b> EN ISO 23999	~ 0.15 %	
<b>Disposal</b>	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203	

**CE** - 18 -

Windmüller GmbH  
Nord-West-Ring 21  
D-32832 Augustdorf

DOP: 0301010  
EN 14041:2004 / AC2006  
1658

R<sub>s</sub>=1 DS E1 HCHO ≤ 2 kV ≥ 0.15 W/(mK)

[www.wineo.de](http://www.wineo.de)

**ÉMISSIONS DANS L'AIR INTÉRIEUR\***

**A+**

Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)

Phthalat frei 100% Phthalate free

**factory made coated**

- Relevant information:**
- R 10 Decor „Heavy Metal“ excluded.
  - Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
  - Residual indentation in combination with silentPREMIUM: see separate data sheet silentPREMIUM.
  - Cleaning and care: see separate cleaning & care instruction.
  - Technical subjects can be changed by Windmüller GmbH.